

## PE Banner - Latex/Solvent & Blockout

### PE - Latex & Solvent

- ★ Indoor/Outdoor
- ★ Billboards
- ★ POP
- ★ Posters

### Features

- ★ Latex/Solvent/Eco-Solvent ink system
- ★ PVC Free
- ★ Recyclable
- ★ Lightweight
- ★ Strong
- ★ Translucent
- ★ REACH Compliant




### Specifications

Material Properties	Weight	Tensile Strength, Grab	Tensile Elongation, Grab	Tear Strength, Tongue	High Temp Shrinkage (100°C/212°F, 1h)	Low Temp Bend	Whiteness	Surface	Coated	
ASTM Test Methods	D751	D5034	D5034	D2261	D1204	D2136	E313	—	—	
120	Metric	120g/m <sup>2</sup>	131 x 79 N/cm	10%	67 x 53 N	≤ 2%	-35°C	85	Glossy/Matt	Yes
	English	3.5 oz/yd <sup>2</sup>	75 x 45 lbs	10%	15 x 12 lbs	≤ 2%	-30°F	85	Glossy/Matt	Yes
160	Metric	160g/m <sup>2</sup>	157 x 131 N/cm	10%	178 x 156 N	≤ 2%	-35°C	85	Glossy/Matt	Yes
	English	4.7 oz/yd <sup>2</sup>	90 x 75 lbs	10%	40 x 35 lbs	≤ 2%	-30°F	85	Glossy/Matt	Yes

### PE - Blockout

- ★ Indoor/Outdoor
- ★ Billboards
- ★ POP
- ★ Posters



### Features

- ★ UV ink system
- ★ PVC Free
- ★ Recyclable
- ★ Lightweight
- ★ Strong
- ★ Translucent
- ★ REACH Compliant

### Specifications

Material Properties	Weight	Tensile Strength, Grab	Tensile Elongation, Grab	Tear Strength, Tongue	High Temp Shrinkage (100°C/212°F, 1h)	Low Temp Bend	Whiteness	Surface	Corona Treatment
ASTM Test Methods	D751	D5034	D5034	D2261	D1204	D2136	E313	—	—
Metric	170g/m <sup>2</sup>	122 x 105 N/cm	10%	156 x 133 N	≤ 2%	-35°C	82	Glossy/Matt	38+ dyne
English	5 oz/yd <sup>2</sup>	70 x 60 lbs	10%	35 x 30 lbs	≤ 2%	-30°F	82	Glossy/Matt	38+ dyne